



Early Journal Content on JSTOR, Free to Anyone in the World

This article is one of nearly 500,000 scholarly works digitized and made freely available to everyone in the world by JSTOR.

Known as the Early Journal Content, this set of works include research articles, news, letters, and other writings published in more than 200 of the oldest leading academic journals. The works date from the mid-seventeenth to the early twentieth centuries.

We encourage people to read and share the Early Journal Content openly and to tell others that this resource exists. People may post this content online or redistribute in any way for non-commercial purposes.

Read more about Early Journal Content at <http://about.jstor.org/participate-jstor/individuals/early-journal-content>.

JSTOR is a digital library of academic journals, books, and primary source objects. JSTOR helps people discover, use, and build upon a wide range of content through a powerful research and teaching platform, and preserves this content for future generations. JSTOR is part of ITHAKA, a not-for-profit organization that also includes Ithaka S+R and Portico. For more information about JSTOR, please contact support@jstor.org.

An account of a sort of Paper made of Linum Asbestinum found in Wales in a Letter to the Publisher, from Edward LLOYD of Jesus Coll. Oxon.

IN obedience to your commands I have here sent you all the account I am able to give at present of the *Lapis Amianthus* or *Linum fossile Asbestinum* which you were inform'd (and that truly) was to be found in the *Isle of Anglesey*: wherein I shall choole to refer it to your own judgment to determine whether this be the same kind with the *Asbestos* of the *Ancients*, or in some respects different from it. Nor shall I mention any thing out of *Authors* relating to it; well knowing that would prove but needless to you, as being not unacquainted with whatever has been said of it: But shall onely give you some bare informations of it from my own *Experience*. It is found in no small quantity in the Parish of *Llan-Fair yng Hornwy* in the Northern part of *Anglesey*; where it runs in veins through a Rock of Stone in hardness and colour not unlike *Flint*. These veins are generally about $\frac{1}{4}$ of an inch deep; which is the length of the *Amiantus*, and is seldome longer, but often shorter. It is compos'd of a *lanuginous* matter exactly resembling that of *pappous Plants*; but so closely compact, that till you draw a Pin, or any such sharp thing, cross the grain of it, it appears onely a shining Stone; there being not the least filament of *lint* to be perceived in it. In its natural form some of it looks *whitish*, and some *Straw-colour'd*, but all shining: but if pounded in a Mortar, the brightness disappears, and the whole becomes *whitish*. Note that above and beneath the veins there's a very thin *septum* of terrene matter between the *Amiantus*, and the Stone whereto it adheres. I put a small quantity of the *lint* in the *fire*, which grew red hot; but though it remain'd there $\frac{1}{4}$ of an hour, I could not perceive that it was any thing consumed. I twist'd some of it also in form of a *Week*, as you had done that

of *Cyprus* before, and dipping it in *Oyl* it gave as good a flame as other *Weeks*, till the *Oyl* was consum'd; the *Week* remaining in the same proportion as at first. Being satisfied it was *incombustible*, and instructed by one of your *Chymical Lectures* in the *Natural History Schoole*, that *Paper* had, and might be made of it, I resolv'd to try whether *any* could be made of *this*; which if not useful, might at least prove surprizing to such as knew not the *material* of it, by its not yielding to the *fire*; to which end I pounded some quantity of it in a *Stone Mortar*, till it became a downy substance and seem'd very fit for that purpose. Then I sifted it through a fine *Searce* by which means I purg'd it indifferent well from its *terrene* parts; for what Earth or Stones I could not pick out of it before, or at the pounding, being reduced to a powder came through the *Searce*, the *Linum* remaining. Having thus pounded it and cleansed it, I brought it to the *Paper-mil*; and putting it in water in a vessel just capacious enough to make Paper with such a quantity; I stirr'd it pretty much, and desired the *workmen* to proceed with it in their usual method of making *Paper*, with their *writing-paper Mould*: onely to stir it about ever before they put their Mould in; considering it as a far more ponderous substance than what they used; and that consequently if not immediatly taken up after it was agitated, it would subside. *Paper* made of it proved but very coarse and too apt to tear, whereof I have sent you a Sheet. But this being the first tryal, I have some reasons to believe it may be much improved; nor did the *workmen* doubt but in case it were pounded in one of their *Mortars* for 20 Hours space it would make good *writing-paper*; which, when I shall receive a sufficient quantity of it, I design to try. In the mean while be pleased to accept of this superficial account of it, in token of gratitude from

Your most oblig'd Servant
E. LLOYD.